

Processing advice

Product name: Fibrolon® P 8540

Date of issue: 03.02.2009

(prev. Fibrolon® 46 N)

Version: 2.0

Page 1 / 2

1. Designation of product, preparation and manufacturer

- 1.1 Trade name: Fibrolon® P 8540 (prev. Fibrolon® 46 N)
- 1.2 Use of product: Natural fibre reinforced compound for injection moulding
- 1.3 Manufacturer: FKUR Kunststoff GmbH
Siemensring 79
D - 47 877 Willich
Phone: + 49 (0) 2154 / 92 51-0
Fax: + 49 (0) 2154 / 92 51-51
Mail: info@fkur.com
Web: www.fkur.com

2. Processing conditions for injection moulding

- 2.1 Machine equipment: Standard screw with non-return flow valve, open nozzle
- 2.2 Machine settings:
- | | | |
|---------------------------|------------|------------|
| Feeding zone | 150 | [°C] |
| Zone 1 | 160 | [°C] |
| Zone 2 | 170 | [°C] |
| Zone 3 | 180 | [°C] |
| Machine nozzle | 180 | [°C] |
| Cylinder kneeling temp. | 140 | [°C] |
| Mass temperature | 170 | [°C] |
| Mould temperature | 30 | [°C] |
| Screw peripheral velocity | up to 150 | [mm/s] |
| Back pressure | up to 50 | [bar] |
| Shot volume | 1 - 3 D | [-] |
| Injection pressure | up to 2000 | [bar] |
| Injection speed | medium | [-] |
| Holding pressure level | 40 - 70 | [%] |
| Holding pressure time | 15 - 30 | [s] |
| Melt cushion (of volume) | 3 - 10 | [%] |
| Cooling time | 10 - 30 | [s] |
| Shrinkage | n/a | [%] |
| Density | 1.05 | [g/cm³] |
| Bulk density | 350 - 400 | [kg/m³] |
| MFR (230 °C/5 kg) | 0.5 - 0.8 | [g/10 min] |
- 2.3. General advice: Process parameters are comparable to PP. We recommend cold runner systems.

3. Purging advice

- 3.1 Before production: Purge the extruder with LDPE, PP or purging compound.
- 3.2 During production: Use sufficient cooling for extruder and tool. If tool is not filled, increase temperature stepwise. Material has a tendency to freeze and need a constant flow.
- 3.3 After production: Purge the extruder with an LDPE, MFR 0.4 - 2.0 [g/10min]. Do not allow material to remain hot inside the extruder for extended periods as the material will degrade.

Processing advice

Product name:

Fibrolon[®] P 8540

Date of issue: 03.02.2009

(prev. Fibrolon[®] 46 N)

Version: 2.0

Page 2 / 2

4. Drying conditions and storage

- 4.1 General: Fibrolon[®] P 8540 is a natural fibre reinforced plastic based on polypropylene. Residual moisture content of more than 0.3 % can result in hydrolysis and evaporation in the injection unit or in condensed moisture on the mould.
- 4.2 Drying: Drying is recommended at 60 °C for a period of 2 - 4 hours.
- 4.3 Storage conditions: It is essential to store the material in a dry and cool place. Opened octabins should be used immediately or adequately resealed to avoid moisture uptake.
- 4.4 Storage conditions for finished products: Finished products made from Fibrolon[®] must be stored dry and cold. It is recommended to seal goods in black PE films to protect them against moisture and UV radiation. Storage time depends on processing parameters and on climate conditions in the respective area. Because of these essential and complex interacting parameters, FKUR Kunststoff GmbH cannot give any shelf life guarantees for finished goods. Please notice that the conditions mentioned above depend on experiences of our customers. Each customer should execute individual storage tests according to product specifications and storage requirements.

5. Legal notice

- 5.1 General: Neither FKUR Kunststoff GmbH nor its marketing affiliates shall be responsible for the use of this information or of any product, method or equipment mentioned. Customers must undertake their own determination of this product's suitability and completeness for their own use, for the protection of the environment, for the health and safety of their employees and purchasers of their products. No warranty is made of the merchantability or fitness of any product, and nothing herein waives any of the seller's conditions of sale.